

CLAIMS

1. ~~A method of forming a capacitor comprising providing a conductive oxide electrode, depositing a first layer of a high dielectric constant oxide dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions, depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, and depositing an upper layer electrode on said second layer of said high dielectric constant oxide dielectric material.~~
2. ~~A method as claimed in claim 1 wherein said high dielectric constant oxide dielectric material is oxidized using a gas plasma.~~
3. ~~A method as claimed in claim 2 wherein said gas plasma is formed from a gas selected from the group consisting of O<sub>2</sub> and O<sub>3</sub>.~~
4. ~~A method as claimed in claim 2 wherein the gas plasma oxidation is carried out at a temperature in the range of from about 250° to about 500°C.~~
5. ~~A method as claimed in claim 1 wherein said high dielectric constant oxide dielectric material is Ta<sub>2</sub>O<sub>5</sub>.~~
6. ~~A method as claimed in claim 5 wherein said high dielectric constant oxide dielectric material is amorphous Ta<sub>2</sub>O<sub>5</sub>.~~
7. ~~A method as claimed in claim 5 wherein said high dielectric constant oxide dielectric material is crystalline Ta<sub>2</sub>O<sub>5</sub>.~~
8. ~~A method of forming a capacitor comprising providing a conductive oxide electrode,~~

Sub  
B1

Sub  
C1

Sub  
C2

09904112-0714060

depositing a first layer of a high dielectric constant oxide dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions,  
5 depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, depositing an upper layer electrode on said second layer of said high dielectric constant oxide dielectric material, and oxidizing said upper layer electrode under oxidizing conditions.

9. A method as claimed in claim 8 wherein said upper layer electrode is oxidized using a gas plasma.

10. A method as claimed in claim 9 wherein said gas plasma oxidation is carried out at a temperature in the range of from about 250° to about 500°C.

11. A method of forming a capacitor comprising providing a conductive oxide electrode, depositing a first layer of a high dielectric constant oxide dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions, depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, depositing an upper layer electrode on said second layer of said high dielectric constant oxide dielectric material, depositing a gas permeable electrode on said upper layer electrode, and oxidizing said upper layer electrode.

12. A method as claimed in claim 11 wherein said gas permeable electrode comprises platinum.

13. A method as claimed in claim 11 wherein said upper layer electrode is oxidized by annealing under oxidizing conditions.

Sub C27

5.07.20 12.07.11 05.07.11

Sub C27

14. A method as claimed in claim 13 wherein said upper electrode is annealed at a temperature in the range of from about 350° to about 500°C.

15. A method of forming a capacitor comprising providing a conductive oxide electrode, depositing a first layer of a high dielectric constant oxide dielectric material comprising Ta<sub>2</sub>O<sub>5</sub> on the conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions, depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, oxidizing said second layer of said high dielectric constant oxide dielectric material, and depositing an upper layer electrode on said second layer of said high dielectric constant oxide dielectric material.

16. A method as claimed in claim 15 wherein said second layer of said high dielectric constant oxide dielectric material is oxidized using a gas plasma.

17. A method as claimed in claim 16 wherein said gas plasma is formed using a gas selected from the group consisting of O<sub>2</sub> and O<sub>3</sub>.

18. A method as claimed in claim 16 wherein said gas plasma oxidation is carried out at a temperature in the range of from about 300° to about 700°C.

19. A method as claimed in claim 15 wherein said second layer of said high dielectric constant oxide dielectric material is oxidized in a furnace.

20. A method as claimed in claim 19 wherein the furnace oxidation is performed at a temperature of less than about 700°C.

0590413-071101

21. A method as claimed in claim 19 wherein the furnace oxidation uses a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

22. A method as claimed in claim 15 wherein said second layer of said high dielectric constant oxide dielectric material is oxidized by rapid thermal oxidation.

23. A method as claimed in claim 22 wherein the rapid thermal oxidation is performed at a temperature of less than about  $700^\circ C$ .

24. A method as claimed in claim 22 wherein the oxidation is performed in the presence of a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

25. A method as claimed in claim 15 further comprising crystallizing said second layer of said high dielectric constant oxide dielectric material prior to depositing said upper electrode.

26. A method as claimed in claim 25 wherein said second layer of said high dielectric constant oxide dielectric material is crystallized by heating said high dielectric constant oxide dielectric material at a temperature greater than about  $700^\circ C$  in an inert atmosphere.

27. A method as claimed in claim 25 wherein said second layer of said high dielectric constant oxide dielectric material is crystallized and oxidized by heating said high dielectric constant oxide dielectric material at a temperature greater than about  $700^\circ C$  in an atmosphere containing a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

28. A method of forming a capacitor comprising providing a conductive oxide electrode, depositing a first layer of a dielectric material comprising  $Ta_2O_5$  on said conductive oxide electrode, treating said conductive oxide electrode and said dielectric

Sub  
C4

0990412-071101

Sub  
a1

5 *Sub*  
*al* material under oxidizing conditions, depositing a second layer of a dielectric material comprising Ta<sub>2</sub>O<sub>5</sub> on said first layer of said dielectric material, oxidizing said second layer of said dielectric material, crystallizing said second layer of said dielectric material, and depositing an upper layer electrode on said second layer of said dielectric material.

*Sub 7*  
*OC* 29. A method as claimed in claim 28 wherein said second layer of said dielectric material is crystallized by heating at a temperature of greater than about 700°C in an inert atmosphere.

30. A method as claimed in claim 28 wherein said second layer of said dielectric material is crystallized and oxidized by heating at a temperature of greater than about 700°C in an atmosphere containing a gas selected from the group consisting of O<sub>2</sub> and N<sub>2</sub>O.

31. A method as claimed in claim 28 wherein said second layer of said dielectric material is oxidized by a gas plasma.

32. A method as claimed in claim 31 wherein said gas plasma oxidation is carried out in a gas selected from the group consisting of O<sub>2</sub> and O<sub>3</sub>.

33. A method as claimed in claim 31 wherein said gas plasma oxidation is carried out at a temperature in the range of from about 300° to about 700°C.

34. A method as claimed in claim 28 wherein said second layer of said dielectric material is oxidized in a furnace.

35. A method as claimed in claim 34 wherein the furnace oxidation is carried out at a temperature less than about 700°C.

0390412-071101  
FOTTE 2770660

36. A method as claimed in claim 34 wherein the furnace oxidation is carried out in an atmosphere containing a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

37. A method as claimed in claim 28 wherein said second layer of said dielectric material is oxidized by rapid thermal oxidation.

38. A method as claimed in claim 37 wherein said rapid thermal oxidation is carried out at a temperature of less than about  $700^\circ C$ .

39. A method as claimed in claim 37 wherein said rapid thermal oxidation is carried out in an atmosphere containing a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

40. A method of forming a capacitor comprising providing a conductive oxide electrode selected from the group consisting of  $RuO_x$  and  $IrO_x$ , depositing a first layer of a dielectric material selected from the group consisting of  $Ta_2O_5$  and  $Ba_xSr_{(1-x)}TiO_3$  on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said dielectric material with a gas plasma, depositing a second layer of said dielectric material on said first layer of said dielectric material, depositing an upper layer electrode on said second layer of said dielectric material, and oxidizing said upper layer electrode.

41. A method as claimed in claim 40 wherein said conductive oxide electrode and said first layer of said dielectric material are oxidized using a gas selected from the group consisting of  $O_2$  and  $O_3$ .

42. A method as claimed in claim 40 wherein the oxidation is carried out at a temperature in the range of from about  $250^\circ$  to about  $500^\circ C$ .

0990413-0740660

- 5

material, oxidizing said second layer of said dielectric material, depositing an upper layer electrode on said second layer of said dielectric material, and oxidizing said upper layer electrode.

51. A method as claimed in claim 50 wherein said second layer of said dielectric material is oxidized with a gas plasma.

52. A method as claimed in claim 51 wherein said gas plasma is formed from a gas selected from the group consisting of  $O_2$  and  $O_3$ .

53. A method as claimed in claim 51 wherein said oxidation is carried out at a temperature in the range of from about  $250^\circ$  to about  $500^\circ C$ .

54. A method as claimed in claim 50 wherein said second layer of said dielectric material is oxidized in a furnace.

55. A method as claimed in claim 54 wherein said furnace oxidation is carried out at a temperature of less than about  $700^\circ C$ .

56. A method as claimed in claim 54 wherein said furnace oxidation is carried out in an atmosphere comprising a gas selected from the group consisting of  $O_2$  and  $N_2O$ .

57. A method as claimed in claim 50 wherein said second layer of said dielectric material is oxidized by rapid thermal oxidation.

58. A method as claimed in claim 57 wherein the oxidation is carried out at a temperature less than about  $700^\circ C$ .

09904112-071101

Sub C6



59. A method as claimed in claim 57 wherein the oxidation is carried out in an atmosphere containing a gas selected from the group consisting of O<sub>2</sub> and N<sub>2</sub>O.

60. A method as claimed in claim 50 wherein said upper layer electrode is oxidized using a gas plasma under oxidizing conditions.

61. A method as claimed in claim 60 wherein the oxidation is carried out at a temperature in the range of from about 250° to about 500°C.

62. A method as claimed in claim 50 further comprising depositing a gas permeable electrode on said upper layer electrode prior to oxidizing said upper layer electrode.

63. A method as claimed in claim 62 wherein said gas permeable electrode comprises platinum.

64. A method as claimed in claim 62 wherein said upper layer electrode is oxidized by annealing under oxidizing conditions.

65. A method as claimed in claim 64 wherein the annealing is carried out at a temperature in the range of from about 350° to about 500°C.

66. A method of forming a capacitor comprising providing a conductive oxide electrode, depositing a first layer of a Ba<sub>x</sub>Sr<sub>(1-x)</sub>TiO<sub>3</sub> dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said dielectric material with a gas plasma under oxidizing conditions, depositing a second layer of said dielectric material on said first layer of said dielectric material, depositing an upper layer electrode on said second layer of said dielectric material, and oxidizing said upper layer electrode.

Sub  
C67

67. A method as claimed in claim 66 wherein said first layer of said dielectric material is deposited at a temperature of less than about 650°C.

68. A method as claimed in claim 66 wherein said first layer of said dielectric material is deposited at a temperature in the range of from about 400° to about 500°C.

69. A method as claimed in claim 66 wherein said conductive oxide electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

70. A method as claimed in claim 66 wherein said first layer of said dielectric material is deposited at a temperature of less than about 650°C.

71. A method as claimed in claim 66 wherein said second layer of said dielectric material is deposited at a temperature in the range of from about 550° to about 600°C.

72. A method as claimed in claim 66 wherein said upper layer electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

73. A method of forming a capacitor comprising providing a conductive oxide electrode depositing a first layer of a high dielectric constant oxide dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions, depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, and depositing an upper layer electrode on said second layer of high dielectric constant oxide dielectric material.

74. A method as claimed in claim 73 wherein said high dielectric constant oxide dielectric material is selected from the group consisting of  $\text{Ta}_2\text{O}_5$  and  $\text{Ba}_x\text{Sr}_{(1-x)}\text{TiO}_3$ .

75. A method as claimed in claim 73 wherein said conductive oxide electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

76. A method as claimed in claim 73 wherein said upper layer electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

77. A method as claimed in claim 73 wherein said high dielectric constant oxide dielectric material is oxidized using a gas plasma.

78. A method as claimed in claim 77 wherein said oxidation is carried out in an atmosphere containing a gas selected from the group consisting of  $\text{O}_2$  and  $\text{O}_3$ .

79. A method as claimed in claim 77 wherein the oxidation is carried out at a temperature in the range of from about  $250^\circ$  to about  $500^\circ\text{C}$ .

80. A capacitor comprising an oxidized conductive oxide electrode, an oxidized first layer of a high dielectric constant oxide dielectric material adjacent said oxidized conductive oxide electrode, a second layer of said high dielectric constant oxide dielectric material adjacent said first layer of said high dielectric constant oxide dielectric material, and an upper layer electrode adjacent said second layer of said high dielectric constant oxide dielectric material, wherein said oxidized conductive oxide electrode and said oxidized first layer of said high dielectric constant oxide dielectric material are oxidized prior to depositing said second layer of said high dielectric constant oxide dielectric material oxide dielectric.

81. A capacitor as claimed in claim 80 wherein said high dielectric constant oxide dielectric material is selected from the group consisting of  $\text{Ta}_2\text{O}_5$  and  $\text{Ba}_x\text{Sr}_{(1-x)}\text{TiO}_3$ .

Sub  
A2

05904112-071101  
5

82. A capacitor as claimed in claim 80 wherein said oxidized conductive oxide electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

83. A capacitor as claimed in claim 80 wherein said upper layer electrode is selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ .

84. A capacitor as claimed in claim 80 further comprising a gas permeable electrode adjacent said upper layer electrode.

85. A capacitor as claimed in claim 84 wherein said gas permeable electrode comprises platinum.

86. A capacitor as claimed in claim 80 wherein said first layer of said high dielectric constant oxide dielectric material is between about 20 and about 50Å thick.

87. A capacitor comprising an oxidized conductive oxide electrode selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ , an oxidized first layer of a high dielectric constant oxide dielectric material adjacent to said oxidized conductive oxide layer, a second layer of said high dielectric constant oxide dielectric material adjacent to said first layer of said high dielectric constant oxide dielectric material, and an upper layer electrode selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$  adjacent said second layer of said high dielectric constant oxide dielectric material, wherein said oxidized conductive oxide electrode and said oxidized first layer of said high dielectric constant oxide dielectric material are oxidized prior to the deposition of said second layer of said high dielectric constant oxide dielectric material.

88. A capacitor as claimed in claim 87 wherein said high dielectric constant oxide dielectric material is selected from the group consisting of  $\text{Ta}_2\text{O}_5$  and  $\text{Ba}_x\text{Sr}_{(1-x)}\text{TiO}_3$ .

09904112-071101

5

10

89. A capacitor as claimed in claim 87 wherein said first layer of said high dielectric constant oxide dielectric material is between about 20 and about 50Å thick.

90. A capacitor comprising an oxidized conductive oxide electrode, an oxidized first layer of a high dielectric constant oxide dielectric material selected from the group consisting of  $Ta_2O_5$  and  $Ba_xSr_{(1-x)}TiO_3$  adjacent said oxidized conductive oxide electrode, a second layer of said high dielectric constant oxide dielectric material adjacent said first layer of said high dielectric constant oxide dielectric material, and an upper layer electrode adjacent said second layer of said high dielectric constant oxide dielectric material, and wherein said oxidized conductive oxide electrode and said oxidized first layer of said high dielectric constant oxide dielectric material are oxidized prior to the deposition of said second layer of said high dielectric constant oxide dielectric material.

91. A capacitor as claimed in claim 90 wherein said oxidized conductive oxide electrode is selected from the group consisting of  $RuO_x$  and  $IrO_x$ .

92. A capacitor as claimed in claim 90 wherein said upper layer electrode is selected from the group consisting of  $RuO_x$  and  $IrO_x$ .

93. A capacitor as claimed in claim 90 further comprising a gas permeable electrode adjacent to said upper layer electrode.

94. A capacitor as claimed in claim 93 wherein said gas permeable electrode comprises platinum.

95. A capacitor as claimed in claim 90 wherein said first layer of said high dielectric constant oxide dielectric material is between about 20 and about 50Å thick.

09904112-071101

96. A capacitor comprising an oxidized conductive oxide electrode selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$ , an oxidized first layer of a high dielectric constant oxide dielectric material selected from the group consisting of  $\text{Ta}_2\text{O}_5$  and  $\text{Ba}_x\text{Sr}_{(1-x)}\text{TiO}_3$  adjacent to said oxidized conductive oxide layer; a second layer of high dielectric constant oxide dielectric material adjacent to said first layer of said high dielectric constant oxide dielectric material, and an upper layer electrode selected from the group consisting of  $\text{RuO}_x$  and  $\text{IrO}_x$  adjacent to said second layer of said high dielectric constant oxide dielectric material, and wherein said oxidized conductive oxide electrode and said oxidized first layer of said high dielectric constant oxide dielectric material are oxidized prior to the deposition of said second layer of said high dielectric constant oxide dielectric material.

97. A capacitor as claimed in claim 96 further comprising a gas permeable electrode adjacent said upper layer electrode.

98. A capacitor as claimed in claim 97 wherein said gas permeable electrode comprises platinum.

99. A capacitor as claimed in claim 96 wherein said first layer of said high dielectric constant oxide dielectric material is between about 20 and about 50Å thick.

100. A method of forming a DRAM cell comprising providing a conductive oxide electrode, depositing a first layer of a high dielectric constant oxide dielectric material on said conductive oxide electrode, oxidizing said conductive oxide electrode and said first layer of said high dielectric constant oxide dielectric material under oxidizing conditions, depositing a second layer of said high dielectric constant oxide dielectric material on said first layer of said high dielectric constant oxide dielectric material, depositing an upper layer electrode on said second layer of said high dielectric constant oxide dielectric material, providing a field effect transistor having a pair of source/drain

09904112-071101

sub  
ble  
ent

regions, electrically connecting one of said source/drain regions with said conductive oxide electrode and electrically connecting the other of said source/drain regions with a bit line.

101. A method as claimed in claim 100 wherein said high dielectric constant oxide dielectric material is oxidized using a gas plasma.

102. A method as claimed in claim 101 wherein said gas plasma is formed from a gas selected from the group consisting of  $O_2$  and  $O_3$ .

103. A method as claimed in claim 101 wherein the gas plasma oxidation is carried out at a temperature in the range of from about  $250^\circ$  to about  $500^\circ C$ .

104. A method as claimed in claim 100 wherein said high dielectric constant oxide dielectric material is  $Ta_2O_5$ .

105. A method as claimed in claim 104 wherein said high dielectric constant oxide dielectric material is amorphous  $Ta_2O_5$ .

106. A method as claimed in claim 104 wherein said high dielectric constant oxide dielectric material is crystalline  $Ta_2O_5$ .

TOP SECRET